



SURFLEX

NON-METALLIC FLOOR HARDENER

DESCRIPTION

SURFLEX is a quartz-silica mixture of finely graded non-metallic aggregates, plasticizer and cement binder. It is an economical concrete floor hardener recommended for both interior and exterior use. It is particularly valuable because of its non-rusting characteristics when floors will be frequently wet. SURFLEX is available in non-fading colors as well as a natural cement color.

PRIMARY APPLICATIONS

- Lobbies and waiting rooms of commercial and public buildings
- Corridors and washrooms in institutional and public buildings
- Auto showrooms and service centers
- Factory and warehouse floors
- Commercial and industrial facilities
- Restaurants and dairies

FEATURES/BENEFITS

- Hardens concrete in one economical operation
- Use of hard and properly graded aggregates increases the wear resistance over plain concrete floors
- Ready-to-use factory blend eliminates messy and expensive job mixing and minimizes errors
- Non-rusting materials make it possible to use SURFLEX outdoors as well as indoors
- Eucon dispersing agent contained in SURFLEX makes it possible to incorporate SURFLEX into the surface of flow slump concretes resulting in exceptionally high surface strengths for maximum wear resistance

TECHNICAL INFORMATION

Typical Engineering Data

Compressive Strength ASTM C 109, (25 mm) cubes Mixed at 2.62 kg of water per 25 kg bag Age Strength MPa

7 days	60
28 days	67.5

Appearance: SURFLEX is a free flowing powder as packaged. It is available in a natural cement color (standard). It is also available in tile red, terra cotta, black, diamond green, french gray, battleship gray, light gray, brown and tan. The final finish can be any texture normally achieved with concrete and should be specified by the owner. In addition, the joints of the newly installed Surfex floor can be filled with a matching color available in the EUCLID QWIKJOINT UVR polyurea joint filler product.

RELATIVE ABRASION RESISTANCE ASTM C 779

Age	Abrasion @ 30 min.	Abrasion @ 60 min.
7 days	0.48 mm	1.07 mm
28 days	0.33 mm	0.91 mm

PACKAGING

SURFLEX is packaged in 25 kg bags with polyethylene liners for moisture protection.

SHELF LIFE

1 year in original, unopened package

COVERAGE

SURFLEX may be applied at rates from 2.4 to 9.8 kg/m². Greater application rates yield better total abrasion resistance, and may be used with special considerations. Contact your Euclid Chemical Company representative for recommended procedures.

SPECIFICATIONS/COMPLIANCES

Canadian Food Inspection Agency

DIRECTIONS FOR USE

The contractor and engineer are encouraged to consult and review the Euclid Chemical bulletin "**Dry Shake Floor Hardeners - Application Instructions**". The document offers instructions detailing the general installation of Euclid Chemical manufactured dry shake floor hardeners. **Note:** *If the contractor is not familiar with the standard application techniques of a dry shake floor hardener, a pre-job meeting is suggested to review the project concrete mix design as well as placement and curing details unique to the particular job. Contact your local Euclid Chemical Company representative for additional information.*

Application Tips: Colored (pigmented) dry shakes require special attention for a uniform color. If the job involves placement of SURFLEX, care should be taken with regards to the following; delay application of the shake as long as possible to get the maximum color saturation at the surface of the slab, apply the shake as evenly as possible and in two applications for maximum uniformity, and do not burnish trowel the floor. Best appearance is achieved by hand troweling the final finish.

Curing and Sealing: After finishing operations are complete and the surface will not be marred by foot traffic, apply a Euclid Chemical curing compound or cure and seal according to product instructions. To produce an exceptionally durable and dustproof surface, cure with a dissipating or removable curing compound such as KUREZ DR VOX or KUREZ RC, then seal with EUCO DIAMOND HARD or ULTRASIL Li+.

CLEAN-UP

Clean tools and equipment with soap and water before material hardens.

PRECAUTIONS/LIMITATIONS

- The use of supplementary cementitious materials are not recommended for use with a dry shake hardener
- Proper curing and sealing is required.
- Sufficient manpower is required to produce consistent results on large placements.
- Important: Air-entraining admixtures may complicate finishing operations and cause blistering. Contact The manufacturer if application of this product will be over air entrained concrete with more than 3% total air content.
- For additional abrasion resistance beyond that offered by SURFLEX, consider the use of EUCO-PLATE HD, an iron aggregate floor hardener.
- Store product in a dry place.
- In all cases, refer the Safety Data Sheet before use.

WARRANTY: Flowcrete India Private Limited solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Flowcrete India Private Limited no other representations or statements made by Flowcrete India or its representatives, in writing or orally, shall alter this warranty. Flowcrete India MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Flowcrete India product fails to conform with this warranty, Flowcrete India will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any installation of Flowcrete India products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Flowcrete India's products for the Buyer's intended purposes.